



Silver-Flakes Ag*

processed by Simoloyer[®]-Technology

Application	Advantages
• effect pigments • thermal / electrical conductivity • powder coatings • decoration / ornaments • ...	• excellent aspect ratio • cost effective • low Fe content

	
typical Ag-flake (SEM)	typical Ag-flake (SEM)

Characteristics		
thickness [µm]	diameter/thickness, ratio	sieve analysis
up to 0,5µm, depends on application	up to 200	100% < 45µm (min)

Packaging: usually in small quantities



technical data subject to alterations